

# SiliFlex Wire & Cable

## SiliFlex Hookup and Multiconductor Cables

#### **FEATURES:**

- Resistant to temperature extremes
- Excellent electrical characteristics
- Easily stripped
- Lightweight
- Corona resistant
- High radiation resistance

### **GENERAL DESCRIPTION**

SiliFlex is distinguished by its extreme limpness and flexibility. It is the most limber of all the High Flex Products offered by Calmont. Silicone rubber insulation compounds are inherently soft and pliable and resists the plastic flow that characterizes many insulation systems. Silicone compounds can be tailored to meet a variety of demands such as extreme high and low temperature requirements, flame resistance, flexibility, radiation resistance, strength and purity.

#### APPLICATIONS

SiliFlex is used extensively for robotic, aerospace and medical applications.

MULTICONDUCTOR JACKET OPTIONS

Silicone 
FEP 
TPE

General Specifications						
ELECTRICAL PROPERTIES	D.C. Volume Resistivity (ohm – CM)	1 x 10 <sup>15</sup>				
	Dielectric Strength (VPM on .075 slab)	550 - 700				
	Dielectric Constant	1000				
	at 60 Hz	2.9 - 3.5				
	Power Factor at 60 Hz	.002004				
	Radiation Resistant (Roentgens)	1 x 10 <sup>8</sup>				
PHYSICAL PROPERTIES	Specific Gravity	1.20 - 1.45				
	Elongation (%)	125 (min.)				
	Shore Hardness (A Scale)	65 (avg.)				
	Tensile Strength (PSI)	800 - 1100				
THERMAL PROPERTIES	Temperature Rating	- 100°F to 400 ° F				
	Estimated Useful Life - at -80 °F	Indefinite				
	- at 250 °F	10 years				
	- at 300 °F	5 years				
	- at 400 °F	2 years				
	- at 500 °F	3 months				
LAME RESISTANCE	Siliflex is available with a self-extinguishing silicone rubber insulation that will pass the Underwriters' Laboratories® VW-1 flame test and the 45° angle flame test of MIL-W-1687					
	Silifley can be manufactured with medical grade silicone compounded under clean					

MEDICAL USAGE

Siliflex can be manufactured with medical grade silicone compounded under clean room conditions. This can be used for medical implantation. To maintain the highest level of purity, the insulation is available nonpigmented (translucent).

Calmont SiliFlex Hookup Wire												
	Bare Copper Conductor					Finished Wire						
Part Number	AWG SIZE	(No. of Stran Strand Size		Conductor Diameter (Nominal)	Conductor A (CM) (Nominal)	reaConductor Resistance (OHMS/1000' N	Current Carr Capacity @ <b>B</b> O <b>(</b> Approxima	) Diameter	Weight (lbs./1000 approxima	Stiffness ) Compariso ate(pounds)		
3006-028-20-1-C-CCC-S	20	105/40	.0031	.039	1038.00	10.00	4.00	.064	4.94	.1400		
3006-028-22-1-C-CCC-S	22	65/40	.0031	.031	642.00	16.10	2.50	.056	3.34	.0500		
3006-028-24-1-C-CCC-S	24	41/40	.0031	.023	405.00	25.60	1.60	.047	2.25	.0200		
3006-028-26-1-C-CCC-S	26	66/44	.0020	.019	258.00	40.20	1.00	.042	1.61	.0090		
3006-028-28-1-C-CCC-S	28	41/44	.0020	.015	160.00	64.70	.60	.038	1.17	.0056		
3006-028-29-1-C-CCC-S	29	51/46	.0016	.014	125.00	82.70	.50	.030	.79	.0040		
3006-028-30-1-C-CCC-S	30	41/46	.0016	.012	100.00	102.80	.40	.028	.67	.0020		
3006-028-32-1-C-CCC-S	32	27/46	.0010	.008	38.00	266.50	.16	.022	.35	.0015		
3006-028-34-1-C-CCC-S	34	40/50	.0010	.006	24.00	426.40	.10	.020	.27	.0012		
3006-028-36-1-C-CCC-S	36	25/50	.0010	.005	16.00	666.20	.60	.019	.22	.0009		
3006-028-38-1-C-CCC-S	38	16/50	.0010	.005	15.57	666.20	.06	.019	.22	.0039		
3006-028-40-1-C-CCC-S	40	12/50	.0010	.003	12.00	888.30	.04	.018	.19	.0008		

<sup>1</sup>Contact Calmont for additional conductor options



Sales@Si-Tech.com.hk